

Drill Hole	From (m)	To (m)	Interval (m)	True Width (m)	Ag (g/t)	Ag (oz/T)
K-11-0358	167.44	170.29	2.85	2.08	33.4	0.97
K-11-0358	178.70	209.17	30.47	22.24	223.6	6.52
K-11-0359	134.35	139.53	5.18	4.22	13.6	0.40
K-11-0359	149.42	154.10	4.68	3.93	18.0	0.53
K-11-0359	156.68	167.06	10.38	8.80	200.8	5.86
K-11-0360	176.25	184.32	8.07	5.89	416.2	12.14
K-11-0360	187.15	189.43	2.28	1.85	19.9	0.58
K-11-0360	192.48	194.00	1.52	1.19	11.1	0.32
K-11-0360	194.66	210.89	16.23	12.72	52.3	1.52
K-11-0361	198.35	202.59	4.24	2.55	78.0	2.28
K-11-0361	205.25	205.70	0.45	0.30	13.9	0.41
K-11-0361	209.43	224.43	15.00	10.13	76.9	2.24
K-11-0361	231.07	232.79	1.72	1.18	193.0	5.63
K-11-0361	237.33	238.04	0.71	0.48	10.1	0.29
K-11-0361	239.00	247.76	8.76	5.78	644.8	18.81
K-11-0363	156.98	159.69	2.71	1.86	22.1	0.64
K-11-0363	190.47	190.71	0.24	0.17	15.7	0.46
K-11-0363	194.00	207.06	13.06	9.00	287.4	8.38
K-11-0363	212.00	213.30	1.30	0.93	10.2	0.30
K-11-0363	215.51	217.25	1.74	1.24	569.3	16.61
K-11-0364	110.00	113.00	3.00	2.41	39.4	1.15
K-11-0364	128.00	131.67	3.67	2.95	141.7	4.13
K-11-0366	118.93	120.20	1.27	0.87	12.0	0.35
K-11-0366	122.00	124.41	2.41	1.65	33.3	0.97
K-11-0368	185.00	200.52	15.52	13.03	61.5	1.79
K-11-0368	204.37	208.81	4.44	3.72	36.8	1.07
K-11-0368	214.28	214.85	0.57	0.45	52.4	1.53
K-11-0369	198.29	222.37	24.08	17.89	248.4	7.24
K-11-0369	231.49	234.96	3.47	2.58	46.1	1.35
K-11-0372	311.17	318.86	7.69	6.42	236.1	6.88
K-11-0372	326.00	327.38	1.38	1.15	16.8	0.49
K-11-0372	329.70	332.00	2.30	1.92	71.9	2.10
K-11-0372	334.45	338.00	3.55	2.97	419.3	12.23
K-11-0372	345.18	354.48	9.30	7.66	229.3	6.69
K-11-0372	363.17	363.42	0.25	0.21	724.0	21.12
K-11-0373	219.37	222.00	2.63	1.94	25.5	0.74
K-11-0373	348.96	350.06	1.10	0.90	315.6	9.21
K-11-0373	354.04	360.17	6.13	5.04	69.0	2.01
K-11-0373	379.70	389.00	9.30	7.39	101.5	2.96
K-11-0373	392.13	392.34	0.21	0.17	11.6	0.34
K-11-0376	287.77	290.00	2.23	1.63	32.7	0.95
K-11-0376	292.50	293.80	1.30	0.95	68.4	1.99
K-11-0376	312.95	316.76	3.81	2.78	12.9	0.38

**Table 3**

**Assay Composites Calculated for Bermingham Drill Holes with assays completed to 30 October 2011**

Using 10 g/t Ag cut-off with a maximum of 2 metres unmineralized internal dilution.

Units	m	metres
	g	gram
	t	tonne
	T	short ton
	%	percent