

Lucky Queen Assay Composites - December 16, 2010

Hole #	From meters	To meters	Length meters	Ag g/tonne	Ag oz/ton	Au g/tonne	Au oz/ton	Pb %	Zn %
K-10-0266	106.74	110.27	3.52	42.9	1.3	0.002	0.000	0.01	0.13
K-10-0266	115.58	119.58	4.00	44.8	1.3	0.060	0.002	0.01	2.09
K-10-0266	207.85	208.55	0.7	81.9	2.4	0.080	0.002	1.02	3.77
K-10-0268	234.49	235.12	0.63	74.8	2.2	0.020	0.001	0.08	0.1
K-10-0269	231.17	234.10	2.93	525.5	15.3	0.093	0.003	1.19	2.50
includes	231.17	232.43	1.26	1095.7	32.0	0.187	0.005	2.03	5.66
K-10-0270	226.09	226.77	0.68	116.0	3.4	0.010	0.000	2.23	0.01
K-10-0270	243.28	244.28	1.00	92.0	2.7	0.005	0.000	0.13	0.47
K-10-0270	245.92	248.72	2.80	150.6	4.4	0.014	0.000	1.22	0.27
includes	246.51	247.85	1.34	259.0	7.6	0.024	0.001	2.41	0.37
K-10-0272	No Significant Mineralization								
K-10-0277	275.14	276.42	1.28	108.2	3.2	0.007	0.000	0.31	0.06
K-10-0277	278.60	278.89	0.29	526.0	16.9	0.450	0.013	23.85	0.20
K-10-0278	230.27	232.67	2.40	1063.6	31.0	0.269	0.008	1.55	0.78
includes	230.27	230.47	0.20	1450.0	42.3	0.140	0.004	15.85	2.92
includes	231.55	232.67	1.12	1877.5	54.8	0.140	0.001	0.25	0.69
K-10-0278	244.20	250.00	5.80	492.1	14.4	0.040	0.001	1.37	0.88
includes	245.37	246.70	1.33	1755.6	51.2	0.079	0.002	4.94	3.25
K-10-0279	244.90	247.05	2.15	843.2	24.6	0.086	0.003	0.52	0.34
includes	246.18	247.05	0.87	1960.0	57.2	0.080	0.002	0.72	0.24
K-10-0280	No Significant Mineralization								
K-10-0282	270.08	270.47	0.39	36.5	1.1	0.005	0.000	0.56	1.07
K-10-0283	160.00	160.88	0.88	168.0	4.9	2.160	0.063	0.06	0.06
K-10-0283	263.04	266.44	3.40	171.4	5.0	0.221	0.006	0.94	0.27
includes	263.70	264.57	0.87	397.8	11.6	0.714	0.021	1.27	0.44
K-10-0288	No Significant Mineralization								
K-10-0294	280.10	280.60	0.50	52.9	1.5	0.005	0.000	0.24	0.23

Composites calculated using a 30 g/tonne Ag cutoff with a maximum 2 meters internal dilution.
Metallurgical recoveries not considered.