

Lucky Queen Exploration DH Assay Composites - November 3, 2009

Area	Hole #	From meters	To meters	Length meters	Ag g/tonne	Ag oz/ton	Au g/tonne	Au oz/ton	Pb %	Zn %
Lucky Queen	K-09-0207	209.70	210.62	0.92	2679.9	78.2	0.170	0.005	5.46	4.57
	includes	209.70	210.00	0.30	8069.0	235.4	0.440	0.013	16.70	13.6
Lucky Queen	K-09-0209	211.95	212.35	0.40	6417.0	187.2	0.580	0.017	3.83	0.48
	K-09-0209	217.80	222.03	4.23	2119.6	61.8	0.159	0.005	5.04	9.66
	includes	218.00	220.98	2.98	2876.0	83.9	0.169	0.005	7.05	8.94
Lucky Queen	K-09-0210	227.90	229.10	1.20	3043.0	88.8	0.120	0.004	9.06	0.66
Lucky Queen	K-09-0213	249.40	250.40	1.00	117.3	3.4	0.015	0.000	1.42	0.51
Lucky Queen	K-09-0215	222.19	224.03	1.84	661.4	19.3	0.08	0.002	4.45	1.05
	includes	222.79	223.10	0.31	3420.7	99.8	0.348	0.010	22.82	4.65
Lucky Queen	K-09-0216	244.10	246.16	2.06	308.9	9.0	0.050	0.001	0.17	0.21
	includes	244.47	245.50	1.03	561.6	16.4	0.063	0.002	0.13	0.37
Lucky Queen	K-09-0217	221.45	222.50	1.05	440.2	12.8	0.038	0.001	4.30	0.02

Note: Composites were calculated using a 30 g/tonne Ag cutoff with a maximum 1 meter internal dilution

