

2010 Onek and Onek North DH Assay Composites - January , 2011

| Area | Hole # | From meters | To meters | Length meters | Ag g/tonne | Ag oz/ton | Au g/tonne | Au oz/ton | Pb % | Zn % | In ppm |
|------------|-----------|-------------------------------|--------------|------------------|---------------|--------------|---------------|--------------|---------|---------|-----------|
| Onek | K-10-0306 | 92.75 | 98.21 | 5.46 | 296.2 | 8.6 | 0.560 | 0.016 | 2.01 | 35.57 | 453 |
| | includes | 93.37 | 94.31 | 0.94 | 1060.0 | 30.9 | 0.770 | 0.022 | 9.36 | 42.02 | 262 |
| Onek | K-10-0308 | 118.94 | 120.00 | 1.06 | 1100.0 | 32.1 | 0.620 | 0.018 | 18.75 | 6.27 | 23 |
| | K-10-0308 | 121.56 | 122.07 | 0.51 | 90.7 | 2.6 | 0.930 | 0.027 | 1.06 | 6.37 | 17 |
| Onek | K-10-0309 | 105.62 | 108.60 | 2.98 | 472.3 | 13.8 | 0.167 | 0.005 | 0.31 | 13.59 | 108 |
| | includes | 105.62 | 106.87 | 1.25 | 1080.1 | 31.5 | 0.346 | 0.010 | 0.57 | 24.83 | 204 |
| Onek | K-10-0311 | 152.89 | 157.21 | 4.59 | 42.9 | 1.3 | 0.188 | 0.005 | 0.35 | 5.36 | 60 |
| | includes | 156.88 | 157.21 | 0.33 | 233.0 | 6.8 | 0.520 | 0.015 | 3.21 | 13.15 | 138 |
| Onek North | K-10-0314 | 88.27 | 89.48 | 1.21 | 65.7 | 1.9 | 0.190 | 0.006 | 0.76 | 0.26 | 32 |
| | K-10-0314 | 91.49 | 93.62 | 2.13 | 80.4 | 2.3 | 0.110 | 0.003 | 0.21 | 0.09 | 8 |
| Onek North | K-10-0316 | No Significant Mineralization | | | | | | | | | |
| Onek North | K-10-0317 | 26.20 | 27.42 | 1.22 | 36.9 | 1.1 | 0.010 | 0.000 | 0.09 | 0.03 | |
| Onek North | K-10-0318 | 231.99 | 232.60 | 0.61 | 43.6 | 1.3 | 0.020 | 0.000 | 0.01 | 0.01 | |
| Onek North | K-10-0322 | No Significant Mineralization | | | | | | | | | |

Composites calculated using a 30 g/tonne Ag cutoff with a maximum 2 meters internal dilution