

2009 Silver King Drillhole Assay Composites

Hole #	From meters	To meters	Length meters	Ag g/tonne	Ag oz/ton	Au g/tonne	Au oz/ton	Pb %	Zn %
K-09-0218	201.85	209.50	7.65	679.0	19.8	0.350	0.010	3.85	0.20
includes	201.85	204.40	2.55	1931.7	56.4	0.935	0.027	11.30	0.41

Note: Composites were calculated using a 30 g/tonne Ag cutoff with a maximum 2 meters internal dilution; metallurgical recoveries not considered.